



CHEMICAL RESISTANT GUIDE

Chemical and Concentration	Part No. Material	RNF15/RNU22 Nitrile	BK Latex	NEO Neoprene	NEOYB Neoprene/Latex
Acetaldehyde			•		
Acetic Acid			•	•	
Acetone 99.5%			•		•
Acetonitrile 99%			•	•	•
Acrylic Acid 99%			•		
Ammonium Fluoride 40%			•	•	•
Ammonium Hydroxide 85%				•	
Amyl Acetate 99%		•			
Amyl Alcohol 99 + %		•		•	
Aniline 99 + %			•		•
Aqua Regia		•	•	•	•
Benzaldehyde 99.5%					
Bromopropionis Acid, Sat.		•		•	
Butyl Acetate 99 + %		•			
Butyl Alcohol 99%		•	•	•	•
Butyl Cellosolve 99 + %		•	•		
Butyrolactone 99 + %				•	
Carbon Disulphide 99%		•	•		
Carbon Tetrachloride 99%		•			
Cellosolve Acetate 99 + %			•		
Chromic Acid 50%		•			
Citric Acid 10%		•	•	•	•
Cyclohexanol 98%		•	•	•	•
Diacetone Alcohol 99%		•	•	•	•
Dibutyl Phthalate 99%		•	•		
Diethylamine 99 + %		•			
Diisobutyl Ketone 80%		•			
Dimethyl Acetamide 99%					•
N,N-Dimethylformamide 99 + %			•		•
Dimethyl Sulfoxide 99 + %				•	
Diocyl Phthalate 99%					•
1,4-Dioxane 99.9%			•		
Epichlorohydrin 99 + %			•		
Ethyl Acetate 99 + %			•		
Ethyl Alcohol 90 + %		•		•	
Ethyl Ether 99 + %		•			
Ethyl Glycol Ether 99%			•	•	•
Ethylene Glycol 99 + %		•		•	•
Formaldehyde 99%		•		•	
Formic Acid 95 + %			•	•	
Furfural 99%			•		
Gasoline, White 100%		•			
Hexamethyldisilazine 97%		•			
Hexane 99 + %		•			
Hydrazine 65%		•		•	
Hydrochloric Acid 10%		•		•	
Hydrochloric Acid 38%		•	•	•	•
Hydrofluoric Acid 48%			•	•	•
Hydrogen Peroxide 30%		•	•	•	•

Chemical and Concentration	Part No. Material	RNF15/RNU22 Nitrile	BK Latex	NEO Neoprene	NEOYB Neoprene/Latex
Hydroquinone, Sat.		•		•	
Isobutyl Alcohol 99%		•	•	•	•
Iso-Octane 99%		•			
Isopropyl Alcohol 99 + %		•	•	•	•
Kerosene 100%		•			
Lactic Acid 85%		•	•	•	
Lauric Acid 36%		•	•		
Maleic Acid, Sat.		•	•	•	•
Methyl Alcohol 99.9 + %			•	•	•
Methylamine 40%		•		•	
Methyl-Butyl Ether 99.8%		•			
Methyl Cellosolve 99%		•		•	
Methyl Ethyl Ketone 99 + %			•	•	
Mineral Spirits, Rule 66. 100%		•			
Monoethanolamine 99 + %		•		•	
Muriatic Acid 100%		•			
Naphtha VM & P 100%		•			
Nitric Acid 10%		•		•	
Nitric Acid 70%			•		
Nitribenzene 99%			•		
Nitromethane 95.5%				•	
Nitropropane 95.5%			•		
Octyl Alcohol 99 + %		•		•	
Oleic Acid 99 + %		•		•	
Oxalic Acid 12.5%		•		•	•
Palmitic Acid, Sat.		•	•	•	•
Pentachlorophenol 35%		•		•	
Pentane 98%		•			
Perchloric Acid 60%		•		•	•
Phenol 90%					•
Phosphoric Acid 85%		•			•
Potassium Hydroxide 50%		•	•	•	
Propyl Alcohol 96 + %		•		•	•
Rubber Solvent 100%		•			
Sodium Hydroxide 50%			•		
Stoddard Solvent 99%		•			
Sulphuric Acid 47%			•	•	•
Sulphuric Acid 95%				•	•
Tannic Acid 37.5%		•			
Thioethyl Alcohol 99%			•		
Thiophene 99%			•		
Toluene 99 + %			•		
Tricresyl Phosphate 90%				•	
Triethanolamine 85%		•			
Turpentine 100%		•			
Xylene 99%		•			

This guide is produced as an aid to selection of hand protective equipment and does not form part of a contract. This information does not release the user of their duties described by Australian Occupational Health and Safety Regulations. It does not override recommendations made in risk assessments or safety data sheets. This information should not be considered a final or authoritative list. Paramount Safety Products accepts no responsibility or liability for loss or injury from the use of equipment that does not comply with the recommendations made to the user following the required OH & S assessment.

Test data is intended as a guide only. It is recommended that you perform your own evaluation based on actual working conditions.